

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

SPONSOR: **Archifibe Inc.**
Mississauga, Ontario, Canada

Sound Absorption
RAL™-A22-072

CONDUCTED: 2022-02-16

Page 1 of 10

ON: ezoCore 25mm

TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as ezoCore 25mm. The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

Product Under Test

Product Name: ezoCore 25 mm
Frame/Edge Description: Exposed Edges
Core Material: Laminated Thermobond and Needlepunched PET Fiber
Nominal Thickness: 25 mm
Panel Dimensions: 1219 mm by 2743 mm
Manufacturer: Archifibe Inc.

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 2 of 10

SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

Test Specimen

Dimensions: 8 panels @ 610 mm (24 in.) by 1372 mm (54 in.)
Thickness: 24.43 mm (0.962 in.)
Overall Weight: 24.04 kg (53 lbs)
Mass per Unit Volume: 147 kg/m³ (9.18 lbs/ft³)

Overall Specimen Properties

Size: 2.44 m (96.0 in) wide by 2.74 m (108.0 in) long
Thickness: 24.43 mm (0.962 in.)
Weight: 24.04 kg (53.0 lbs)
Mass per Unit Area: 3.59 kg/m² (0.74 lbs/ft²)
Calculation Area: 6.689 m² (72. ft²)

Test Environment

Room Volume: 291.98 m³
Temperature: 20.6 °C ± 0.5 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)
Relative Humidity: 59.85 % ± 0.9 % (Requirement: ≥ 40 % and ≤ 5 % change)
Barometric Pressure: 98.0 kPa (Requirement not defined)

MOUNTING METHOD

Type D-50 Mounting: The test specimen was mounted on 51 mm (2 in.) thick wood furring strips spaced approximately 305 mm (12 in.) on centers and laid directly against the test surface. The furring strips produced a 51 mm (2 in.) thick air space behind the test specimen. Perimeter edges were sealed with wood and metal framing and tape.

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 3 of 10



Figure 1 – Specimen mounted in test chamber



Figure 2 – Wood furring spacers in test chamber prior to installation of test specimen

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 4 of 10



Figure 3 – Individual specimen panel



Figure 4 – Specimen partially installed over spacers

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 5 of 10



Figure 5 – Detail of specimen materials and airgap depth

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

Archifibe Inc.
 2022-02-16

RAL™-A22-072
 Page 6 of 10

TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

1/3 Octave Center Frequency (Hz)	Total Absorption (m ²)	Total Absorption (Sabins)	Absorption Coefficient
100	2.13	22.95	0.32
** 125	2.69	28.93	0.40
160	2.64	28.38	0.39
200	3.61	38.88	0.54
** 250	4.35	46.83	0.65
315	6.01	64.73	0.90
400	6.55	70.48	0.98
** 500	7.18	77.25	1.07
630	7.28	78.37	1.09
800	7.56	81.36	1.13
** 1000	7.82	84.17	1.17
1250	7.78	83.75	1.16
1600	7.43	80.00	1.11
** 2000	7.37	79.34	1.10
2500	7.12	76.68	1.07
3150	7.28	78.34	1.09
** 4000	7.06	75.98	1.06
5000	7.16	77.08	1.07

SAA = 1.00
NRC = 1.00

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 7 of 10

TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-17 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by 
Marc Sciaky
Senior Experimentalist

Report by 
Keith Kimberling
Associate Test Engineer

Approved by 
Eric P. Wolfram
Laboratory Manager

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE


Archifibe Inc.
2022-02-16

RAL™-A22-072

Page 8 of 10

SOUND ABSORPTION REPORT

ezoCore 25mm



SAA = 1.00

NRC = 1.00



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

Archifibe Inc.
 2022-02-16

RAL™-A22-072
 Page 9 of 10

APPENDIX A: Extended Frequency Range Data

Specimen: ezoCore 25mm (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

1/3 Octave Band Center Frequency (Hz)	Total Absorption (Sabins)	Absorption Coefficient
31.5	5.95	0.08
40	5.80	0.08
50	14.21	0.20
63	5.19	0.07
80	13.10	0.18
100	22.95	0.32
125	28.93	0.40
160	28.38	0.39
200	38.88	0.54
250	46.83	0.65
315	64.73	0.90
400	70.48	0.98
500	77.25	1.07
630	78.37	1.09
800	81.36	1.13
1000	84.17	1.17
1250	83.75	1.16
1600	80.00	1.11
2000	79.34	1.10
2500	76.68	1.07
3150	78.34	1.09
4000	75.98	1.06
5000	77.08	1.07
6300	77.60	1.08
8000	82.82	1.15
10000	78.62	1.09
12500	81.73	1.14

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Archifibe Inc.
2022-02-16

RAL™-A22-072
Page 10 of 10

APPENDIX B: Instruments of Traceability

Specimen: ezoCore 25mm (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2021-07-01	2022-07-01
Bruel & Kjaer Mic And Preamp A	Type 4943-B-001	2311428	2021-07-13	2022-07-13
Bruel & Kjaer Pistonphone	Type 4228	2781248	2021-08-13	2022-08-13
EXTECH Hygro 999	SD700	A.106999	2021-05-11	2022-05-11

APPENDIX C: Revisions to Original Test Report

Specimen: ezoCore 25mm (See Full Report)

<u>Date</u>	<u>Revision</u>
2021-02-18	Original report issued

END