

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

FOR: **ezoBord**
Elgin, IL

Sound Absorption
RAL™-A18-336

CONDUCTED: 2018-10-04
ON: ezoBord Panel 3/8 in. (9 mm)

Page 1 of 7

TEST METHOD

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2005 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measuring procedure and room qualifications is available upon request.

DESCRIPTION OF THE SPECIMEN

The test specimen was designated by the manufacturer as ezoBord Panel 3/8 in. (9 mm). A full external visual inspection performed on the test specimen by Riverbank personnel verified the manufacturer's description.

Test Specimen

Materials: Polyethylene terephthalate
Dimensions: 2 @ 2438.4 mm (96 in.) x 1219.2 mm (48 in.)
Thickness: 9.14 mm (0.36 in.)
Overall Weight: 14.97 kg (33 lbs)

Physical Measures

Size: 2.44 m (96.0 in) wide by 2.44 m (96.0 in) long
Thickness: 9.14 mm (0.36 in.)
Weight: 7.71 kg (17.0 lbs)
Mass per Unit Area: 1.3 kg/m² (0.27 lbs/ft²)
Calculation Area: 5.946 m² (64 ft²)

Test Environment

Room Volume: 291.98 m³
Temperature: 20.9 °C ± 0.1 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)
Relative Humidity: 62.45 % ± 0.3 % (Requirement: ≥ 40 % and ≤ 5 % change)
Barometric Pressure: 99.4 kPa (Requirement not defined)

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An **ALION** Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

ezoBord
2018-10-04

RAL™-A18-336
Page 2 of 7




Figure 1 – Specimen mounted in test chamber



Figure 2 – Detail of specimen material

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

Test Report

ezoBord
 2018-10-04

RAL™-A18-336

Page 3 of 7

MOUNTING METHOD

Type A Mounting: The test specimen was laid directly against the test surface. The perimeter edges were exposed, as would be typical of an actual installation of this specimen.

TEST RESULTS

1/3 Octave Center Frequency (Hz)	Total Absorption (m ²)	Total Absorption (Sabins)	Absorption Coefficient
100	0.02	0.26	0.00
** 125	0.97	10.43	0.16
160	0.52	5.63	0.09
200	0.26	2.85	0.04
** 250	0.34	3.63	0.06
315	0.50	5.37	0.08
400	0.60	6.41	0.10
** 500	1.01	10.87	0.17
630	1.31	14.13	0.22
800	1.72	18.51	0.29
** 1000	2.40	25.87	0.40
1250	2.80	30.16	0.47
1600	3.35	36.06	0.56
** 2000	3.69	39.69	0.62
2500	3.96	42.61	0.67
3150	4.34	46.76	0.73
** 4000	4.69	50.44	0.79
5000	5.09	54.80	0.86

SAA = 0.31

NRC = 0.30

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

ezoBord
2018-10-04

RAL™-A18-336
Page 4 of 7

TEST RESULTS (Continued)

The sound absorption average (SAA) is defined in ASTM C423-17 Section 3.1.1 as the average, rounded to the nearest integer multiple of 0.01, of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, expressed to the nearest integer multiple of 0.05.

Tested by 
Dean Victor
Senior Experimentalist

Report by 
Malcolm Kelly
Acoustician

Approved by 
Eric P. Wolfram
Laboratory Manager

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report


ezoBord
2018-10-04

RAL™-A18-336

Page 5 of 7

SOUND ABSORPTION REPORT

ezoBord Panel 3/8 in. (9 mm)



SAA = 0.31

NRC = 0.30

1512 S BATAVIA AVENUE
 GENEVA, IL 60134
 630-232-0104

An  ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
 WALLACE CLEMENT SABINE

Test Report

ezoBord
 2018-10-04

RAL™-A18-336

Page 6 of 7

APPENDIX A: Extended Frequency Range Data

Specimen: ezoBord Panel 3/8 in. (9 mm) (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

1/3 Octave Band Center Frequency (Hz)	Total Absorption (Sabins)	Absorption Coefficient
31.5	-10.36	-0.16
40	6.76	0.11
50	4.44	0.07
63	-6.15	-0.10
80	-1.12	-0.02
100	0.26	0.00
125	10.43	0.16
160	5.63	0.09
200	2.85	0.04
250	3.63	0.06
315	5.37	0.08
400	6.41	0.10
500	10.87	0.17
630	14.13	0.22
800	18.51	0.29
1000	25.87	0.40
1250	30.16	0.47
1600	36.06	0.56
2000	39.69	0.62
2500	42.61	0.67
3150	46.76	0.73
4000	50.44	0.79
5000	54.80	0.86
6300	56.88	0.89
8000	68.03	1.06
10000	66.66	1.04
12500	69.86	1.09



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2005 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE
GENEVA, IL 60134
630-232-0104

An ALION Technical Center

RIVERBANK.ALIONSCIENCE.COM

FOUNDED 1918 BY
WALLACE CLEMENT SABINE

Test Report

ezoBord
2018-10-04

RAL™-A18-336

Page 7 of 7

APPENDIX B: Instruments of Traceability

Specimen: ezoBord Panel 3/8 in. (9 mm) (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-4/2	3160-106968	2018-08-09	2019-08-09
Bruel & Kjaer Mic And Preamp C	Type 4943-B-001	2311439	2018-03-27	2019-03-27
Bruel & Kjaer Pistonphone	Type 4228	2781248	2018-08-06	2019-08-06
Omega Digital Temp., Humid. And Pressure Recorder	OM-CP-PRHTemp2000	P97844	2018-02-03	2019-02-03

END